

Manchester Brick Handmade Barcombe Blend Bricks - Pallet of 640no

Our Ref: 18609

Price : £114.00 inc VAT.

Website : [Click here to view this item on our website](#)

If you have any questions please do not hesitate to contact us





















MANCH
ESTD
BRICK
SPECIALISTS
641 3579
TERBRICK.COM
Sedex Member





product name	Production location	
Handmade BARCOMBE BLEND	Erbaa/Tokat	
Colour		
Red with dark shades		
Format		
Moulding method	Hand form	
DF: 215 x 100 x 65 mm	Between batches the average size and color may slightly differ	
Essential Characteristics - EN771-1		
CE NPD		
Dimensional tolerances	T1	
Range	R1	
Active Soluble Salts	S2	
Mean Compressive strength	$\geq 20 \text{ N/mm}^2$	Tested to the bed face
Normalized Compressive strength	NPD	Tested to the bed face
Dimensional stability	NPD	
Bond Strength general	$0,15 \text{ N/mm}^2$	
Bond Strength in layer	$0,30 \text{ N/mm}^2$	
Reaction to fire	A1	Category
Water absorption	$\leq 15\% \text{ m/m}$	
Water vapour permeability	5/10	
Net dry density	$1610 \text{ kg/m}^3 \text{ (D1)}$	
Gross dry density	$1720 \text{ kg/m}^3 \text{ (D1)}$	
Thermal conductivity Lambda 50/100	$\leq 0,41 \text{ W/m.K}$	
Durability against freeze thaw	F2	
Other Characteristics		
Initial rate of water absorption - Non-coated Bricks	1,5 - 4,0 $\text{kg/m}^2 \cdot \text{min (W3)}$	Value according EN771-1 2011 - 5.3.8
Initial rate of water absorption - Coated bricks	NPD	Value according EN771-1 2011 - 5.3.8
Freeze/thaw resistance	NPD	B-27-009
Thermal conductivity Lambda 50/100	NPD	
Thermal conductivity Lambda 100	NPD	
Thermal conductivity Lambda 200	NPD	

PRODUCT TECHNICAL INFORMATION SHEET

Barcombe Blend

STEEL STOCKISTS • INDUSTRIAL REMOVALS
METAL MERCHANTS • SECURE SITE UNITS

WWW

